

# TECHNICAL DATA SHEET

SL.NO.	CHARACTERISTICS	GUARANTEED	TYPICAL
01	Texture	Soft dry Powder	Soft dry Powder
02	pH (20% pigment slurry)	6.5 to 8.0	7.60
03	Volatile Matter, % By Mass	0.50, max	0.26
04	Residue, % By Mass (45 $\mu$ Sieve)	0.1, max	0.09
05	Oil Absorption, % By Mass	20 to 30	25
06	Soluble salt , % By Mass	0.50, max	0.38
07	Tinting Strength	1200, min	1230
08	TiO <sub>2</sub> , % By Mass	98.00, min	98.20
09	Specific Gravity	3.80	3.80
10	Iron, ppm	100, max	56